

RELMAT SOLID WOOD FLOORING

ZEUS LINE

- TEAK -

TECHNICAL SPECIFICATIONS

1. General Technical Characteristics of RELMAT ZEUS Line

ZEUS Line of RELMAT consists of a series of prefinished hardwood floors that come from natural wood and can be offered in several species (Oak, Kempas, Merbau, Teak, Bamboo). The choice for a wooden floor usually depends on the desired colour as well as the use of the area.

With tongue & groove system, cut by diamond-tip tooling, RELMAT Solid Parquet gives a uniform and stable fit whether you nail, glue or float the installation.

As a prefinished product, the varnish is laid on all sides of the plank and under the following structure: 5 layers, plus 2 layers from Aluminum Oxide on the top surface and 2 layers on the bottom and the sides. The main reason for this structure is to ensure the total protection of the parquet, as the varnish - made from German company TREFFERT - is known for providing:

1. Resistance to scratches
2. Resistance to moisture
3. Protection against wood bacteria
4. Impact resistance
5. Resistance to household materials, stains, etc
6. Resistance to cigarette burns
7. Resistance to UV rays





1.2 TEAK - The tree

Scientific Name: *TECTONA GRANDIS*

Teak is a tree of the tropical zone that grows in Burma and India. With its height ranging from 39 to 45m and its diameter from 90 to 150m, it is considered a big tree.

Teak is well-known for its great dimensional stability and its unique gold to brownish color. The wood has significant durability due to the large content in natural teak oil

2. Dimensions of RELMAT Solid Teak

Width:	123mm
Length:	910mm
Thickness:	18mm
Grade:	GRADE A
Edges:	TONGUE AND GROOVE (T & G), width of tongue: 4.58mm

3. Technical Specifications of RELMAT Solid Teak

Moisture Content	10-12%
Gloss Degree	40.2%
Density (g/cm ³) *	0.67
Crushing strength * (MPa)	56
Static bending strength * (MPa)	98
Modulus of Elasticity * (MPa)	13.740
Hardness Janka	1000

***: at 12% moisture content; 1 MPa = 1N/mm²**

Source: CIRAD Forestry Department, National Wood Floor Association



Technical Specifications of TREFFERT Varnish

Test	Standard	Classification
Acetic acid 5%	20min	5
Ammonia 10% sol	960' (16h)	5
Ethylacohol 50%	1440' (24h)	5
Coffee	960' (16h)	5
Water	1440' (24h)	5
Acetone	960' (16h)	5
Mustard	1440' (24h)	5
NaOH 25% sol	10min	5
Adhesion	Cross-cut EN ISO 2409 Cross- cut and adhesive tape	0
Resistance to surface wear	(PrEN13329) S42 revolutions to IP	400
	(ASTM4060)CS17 revolution to IP	>15000
	Wear-Index mg abr./1000cycles	35
Resistance to impact	By small diameter ball EN 438-2.11(N)	<3
Resistance to scratching	EN 438-2.14(N)	2
Flammability	DIN 51960	K1

Test Results of RELMAT Solid Parquet

Formaldehyde	mg/100cm ² /day in 35°C	< 0,05
Arsenic	mg/kg	< 0,05

*** The tests were conducted in a Certified Laboratory**